



HIGH TEMPERATURE, MAGNETICALLY LOADED ABSORBER

Rigid, magnetically loaded, injection moldable load absorber. Typically used as attenuators and terminations in microwave transmission lines such as for waveguide, coaxial or stripline applications. Other applications include phase shifters in phased array antennas and board level absorber covers that result in EMI reduction through combination of absorption and shielding. Available in two grades or loading levels: MF-PPS-120 and MF-PPS-124. These grades pass UL94 V0 requirements.

FEATURES AND BENEFITS

- Thermoplastic polymer amenable to injection molding processes
- Injection molding is ideal for complex shapes and high volume applications - results in lower part cost
- High service temperature of polymer is amenable to solder reflow processes
- Environmentally friendly and meets RoHs and REACH requirement
- Passes UL94 V0 testing
- Low outgassing - < 1.00% TML and <0.10% CVCM

MARKETS


- Telecom infrastructure and wireless networks
- Satellite communications
- Automotive radar
- Military electronics
- Industrial instrumentation
- Medical

TYPICAL PROPERTIES	ECCOSORB MF-PPS
Density (g/cc)	4.48-4.66
Tensile Strength (psi)	8,000
Hardness (Shore D)	92
Max Service Temperature (°C)	210
Surface Resistivity (Ohm/Square)	10 ¹¹
Water Absorption (%)	<0.01%
Thermal Conductivity (W/m-K)	1.2
Dielectric Breakdown (Volt/mil)	6.2

MATERIAL CHARACTERISTICS AND RELATED PRODUCTS

Rigid, magnetically loaded absorbers have cost advantage in high volume applications or for complex shapes that would otherwise be cost prohibitive as machined parts. Thermoplastic injection molded absorbers generally have low shrinkage (<0.3%). When part is complex in shape, lower MOQs can be economical to produce. DXF-drawing files are needed for optimization of mold design.

Eccosorb MF-PPS has equivalent magnetic and dielectric properties to comparably loaded thermoset absorbers in the Eccosorb MF, MF500F and MFS product lines. See graph below for attenuation properties of MF-PPS as a function of frequency.



RFP-DS-MF-PPS 112315

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.